

(12) United States Patent

Langford

US 7,048,791 B2 (10) Patent No.:

(45) Date of Patent: *May 23, 2006

(54) LOW DUST WALL REPAIR COMPOUND

(75) Inventor: Nathaniel P. Langford, Somerset, WI

Assignee: 3M Innovative Properties Company,

St. Paul, MN (US)

Subject to any disclaimer, the term of this (*) Notice:

patent is extended or adjusted under 35

U.S.C. 154(b) by 0 days.

This patent is subject to a terminal dis-

claimer.

(21) Appl. No.: 11/072,083

Filed: Mar. 4, 2005 (22)

(65)**Prior Publication Data**

> US 2005/0193922 A1 Sep. 8, 2005

Related U.S. Application Data

- (60) Division of application No. 10/788,053, filed on Feb. 26, 2004, now Pat. No. 6,863,723, which is a division of application No. 09/821,392, filed on Mar. 29, 2001, now Pat. No. 6,733,581, which is a continuation-inpart of application No. 09/208,782, filed on Dec. 10. 1998, now Pat. No. 6,358,309.
- (51) Int. Cl. C04B 24/02 (2006.01)(2006.01) C04B 24/08 C04B 24/14 (2006.01)
- (52) **U.S. Cl.** 106/250; 106/251; 106/267; 106/504; 106/657; 106/659; 106/661; 106/665; 106/822; 252/88.1; 524/2; 524/476; 524/481; 524/483
- Field of Classification Search 106/250, 106/251, 267, 504, 657, 659, 661, 665, 822; 252/88.1; 524/2, 476, 481, 483

See application file for complete search history.

(56)References Cited

U.S. PATENT DOCUMENTS

3,984,269 A	10/1976	Schneller et al.
4,038,443 A	7/1977	Jacoby
4,136,050 A	1/1979	Brehm
4,171,276 A	10/1979	Brehm
4,238,239 A	12/1980	Brown
4,269,721 A	5/1981	Mueller et al.
4,286,995 A	9/1981	Smith et al.
4,294,622 A	10/1981	Brown
4,316,811 A	2/1982	Burns et al.
4,369,121 A	1/1983	Callahan et al.
4,370,167 A	1/1983	Mudd
4,380,459 A	4/1983	Netting

(Continued)

FOREIGN PATENT DOCUMENTS

CA1117989 2/1982

(Continued)

Primary Examiner—Kelechi C. Egwim (74) Attorney, Agent, or Firm—David B. Patchett

ABSTRACT

A wall repair compound useful for filling and repairing cracks, holes, and other imperfections in a wall surface includes a conventional filler material, a conventional binder material, and a dust reducing additive which reduces the quantity of airborne dust particles generated when sanding the hardened joint compound. Airborne dust reducing additives include oils, surfactants, solvents, waxes, and other petroleum derivatives. The additive can be added to conventional ready-mixed joint compounds and to setting type joint compounds. A method of reducing the quantity of airborne dust generated when sanding a fully hardened joint compound includes mixing a sufficient quantity of the dust reducing additive with the joint compound prior to when the joint compound has been applied to the wall.

10 Claims, 1 Drawing Sheet

